

Technical Datasheet

Liquid Coating Resins and Additives

ACROMUL® 570WG

Edition 04-2020

Acromul® 570WG is a 50% solids content Styrene Acrylic copolymer water-dispersion containing anionic surfactants.

Stabilizer: Surfactants

Compatibility with mineral charges: Excellent

1. SUPPLY SPECIFICATIONS

• Solid content 50 ± 1 %

Brookfield viscosity @ 20 °C
7,000 ± 2,000 mPa.s

• pH 8.0 ± 0.5

2. TYPICAL VALUES

• Minimum film-forming temperature $20.0 \pm 1.0 \,^{\circ}\text{C}$

Prevailing particle size range
0.05 Microns

Dispersing system anionic - non ionic

• Density at 23°C 1.06

Mechanical stability
Excellent

APPLICATIONS

Indoor and outdoor water based paints and wall textured coatings and primers.

SPECIFIC PROPERTIES

ACROMUL® 570WG is a fine particle size Styrene Acrylic Emulsion, supplied at 50% solids content for the formulation of interior and exterior emulsion paints, primers, undercoats, putties, etc. to be applied on mineral substrates such as masonry, plasters, fibre cement and concrete.

ACROMUL® 570WG, demonstrates wide formulation latitude from gloss through semi-gloss to matt paints with a markable washability range, which is suitable for both interior and exterior applications. The hardness level of this binder makes ACROMUL® 570WG suitable for miscellaneous applications such as interior undercoats and wall paints making it a truly general purpose or so called "universal" binder for paint companies wishing to minimise the number of raw materials.

PACKAGING

ACROMUL® 570WG is available in bulk and in IBC's, 160kg, 150kg, 125 Kg or 50 Kg drums.

STORAGE

ACROMUL® 570WG is stable for at least 12 months when stored between +5°C and +35°C.

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.