

# **Technical Datasheet**

Liquid Coating Resins and Additives

# Solvoya® D6546-X TFA

Edition 04-2020

Solvoya® D6546-X TFA is a chain stopped short oil air-drying alkyd resin based on low rosin tall oil F.A - available in solids of 50.0±1.0% in xylene. Mode of application: Air physical dry, Nitrocellulose and catalyzed drying.

## **PERFORMANCE & APPLICATIONS**

- Chain stopped
- Excellent salt spray resistance
- Extremely fast dry with good adhesion to metal
- Automotive refinishing enamels
- Excellent isolating varnish & wire enamels

- Corrosion resistance primers
- White air drying & stoving finishes
- 2K PU for wood finish
- Road Marking paints
- Recommended for improving curing of NC-sealer

#### **SUPPLY SPECIFICATIONS**

- Delivery form
- Dilution form
- Gardner viscosity at 25°C
- Brookfield approx. viscosity at 25°C
- Gardner Color Scale DIN EN ISO 6271-1
- Acid value mg KOH/gm solid
- OH Content (per solid)

- 50.0 ± 1.0%
- 50.0 ± 1.0%
- Y-Z at 50.0%
- Approx. 1800 CP at 50%
- 6.0 max.
- 12.0 max.
- 3.00%

#### TYPICAL COMPOSITION

- Phthalic anhydride content
- Type of oil
- Oil Content
- Type of Solvent(s)
- Type of Polyol

- 26%
- Low rosin tall oil F.A
- 36%
- Penta
- Xylene

#### SPECIFIC PROPERTIES

- Aliphatic hydrocarbon Aromatic hydrocarbon
- Chlorinated hydrocarbon

Glycol-ethers & esters

- Alcohols Esters
- Ketones

- Insoluble
- Soluble
- Limited solubility
- Insoluble
- Soluble
- Soluble Soluble

- Zinc white • Red Lead
- Nitrocellulose
- Chlorinated rubber
- Stand oil
- Isocyanate

Urea/melamine resins

Incompatible Compatible

Limited compatibility

- Limited compatibility
- Incompatible Limited compatibility
- Limited compatibility

#### **STORAGE**

Solvoya® D6546-X TFA is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

### **STABILITY**

Solvoya® D6546-X TFA is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

# **REMARKS**

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.