

Technical Datasheet

Liquid Coating Resins and Additives

Solvoya® D68145-X

Edition 04-2020

Solvoya® D68145-X is a chain stopped short oil air-drying alkyd resin based on Linseed oil - available in solids from 50% to 55.0±1.0% in xylene.

Mode of application: Air physical dry, Nitrocellulose and catalyzed drying.

PERFORMANCE & APPLICATIONS

- Chain stopped
- Excellent salt spray resistance
- Extremely fast dry with good adhesion to metal
- Good gloss & color retention
- Very good yellowing resistance

- Corrosion resistance primers
- 2K PU for wood finish
- Recommended for isolating varnish & wire enamels
- Automotive refinishing enamels

SUPPLY SPECIFICATIONS

- Delivery form
- Dilution form
- Gardner viscosity at 25°C
- Brookfield approx. viscosity at 25°C
- Gardner Color Scale DIN EN ISO 6271-1
- Acid value mg KOH/gm solid
- OH Content (per solid)

- 55.0 ± 1.0% 55.0 ± 1.0%
- Approx. Z6 at 55%
- Approx. 14,500 CP at 55%
- 6.0 max.
- 10.0 max.
- 3.9%

TYPICAL COMPOSITION

- Phthalic anhydride content
- Type of oil Oil Content
- Type of Polyol
- Type of Solvent(s)

36%

- Linseed oil
- 32%
- Penta
- Xylene

SPECIFIC PROPERTIES

| Aliphatic hydrocarbon | |
|---|--|
| Aromatic hydrocarbon | |
| Chlorinated hydrocarbon | |

- Alcohols
- Esters Ketones
- Glycol-ethers & esters

- Insoluble
- Soluble
- Limited solubility
- Insoluble
- Soluble Soluble

Soluble

- Zinc white
- Red Lead
- Nitrocellulose
- Chlorinated rubber
- Stand oil
- Isocyanate
- Limited compatibility Incompatible
- Limited compatibility Urea/melamine resins Limited compatibility

Limited compatibility

Incompatible

Compatible

STORAGE

Solvoya® D68145-X is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

STABILITY

Solvoya® D68145-X is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

REMARKS

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.