

# Technical Datasheet

Liquid Coating Resins and Additives

# Solvoya® L4299-W

Edition 04-2020

Solvoya® L4299-W is Long oil alkyd resin based on Low rosin tall oil F.A - available in solids from 70% to 99% in white spirit.

Mode of application: Air physical dry

#### PERFORMANCE & APPLICATIONS

- Medium viscosity paints
- Very high Gloss enamel
- Varnish & floor sealers

- Good gloss & gloss retention
- Good brushability & leveling
- Light color
- Excellent yellowing resistance

# **SUPPLY SPECIFICATIONS**

| <ul> <li>Delivery for</li> </ul> | rm |
|----------------------------------|----|
|----------------------------------|----|

Dilution form

Acid value mg KOH/gm solid

Gardner viscosity at 25°C

Brookfield approx. viscosity at 25°C (55%)

• Gardner Color Scale DIN EN ISO 6271-1

#### 70.0 ± 1%

70.0 ± 1%

10.0 max.

Z5 at 70%

Approx. 9900 CP at 70%

5.0 max.

### TYPICAL COMPOSITION

Phthalic anhydride content

Type of oil

 Oil Content Type of Polyol

Type of Solvent(s)

23%

Low rosin tall oil F.A

Urea/melamine resins

58%

Penta

White spirit

#### SPECIFIC PROPERTIES

| <ul> <li>Aliphatic hydrocarbon</li> </ul>    | Soluble   |
|--|-----------|
| <ul> <li>Aromatic hydrocarbon</li> </ul>     | Soluble   |
| <ul> <li>Chlorinated hydrocarbon</li> </ul>  | Soluble   |
| • Alcohols                                   | Insoluble |
| • Esters                                     | Soluble   |
| • Ketones                                    | Soluble   |
| <ul><li>Glycol-ethers &amp; esters</li></ul> | Soluble   |
|  |           |

Zinc white Compatible Red Lead Compatible Nitrocellulose Incompatible Chlorinated rubber Compatible Stand oil Compatible Isocvanate Incompatible

#### **STORAGE**

Solvoya® L4299-W is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

# **STABILITY**

Solvoya® L4299-W is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

# **REMARKS**

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.

Incompatible