# **Technical Datasheet**

# Solvoya<sup>®</sup> L3250-ECO

Solvoya<sup>®</sup> L3250-ECO is *Chain stopped* long oil alkyd resin based on Soya bean oil or Soya Fatty Acid - available in solids from 55% to 70% in W.Spirit.

Mode of application: Air physical dry

#### **PERFORMANCE & APPLICATIONS**

- Interior & exterior decorative paints
- Very fast drying time
- Very high Gloss enamel
- Varnish & floor sealers

#### SUPPLY SPECIFICATIONS

- Delivery form
- Dilution form
- Acid value mg KOH/gm solid
- Gardner viscosity at 25°C
- Brookfield approx. viscosity at 25°C (55%)
- Gardner Color Scale DIN EN ISO 6271-1

#### **TYPICAL COMPOSITION**

- Phthalic anhydride content
- Type of oil
- Oil Content
- Type of Polyol
- Type of Solvent(s)

#### SPECIFIC PROPERTIES

| <ul> <li>Aliphatic hydrocarbon</li> </ul>   | Soluble   | Zinc white                               | Compatible   |
|---------------------------------------------|-----------|------------------------------------------|--------------|
| <ul> <li>Aromatic hydrocarbon</li> </ul>    | Soluble   | Red Lead                                 | Compatible   |
| <ul> <li>Chlorinated hydrocarbon</li> </ul> | Soluble   | Nitrocellulose                           | Incompatible |
| Alcohols                                    | Insoluble | <ul> <li>Chlorinated rubber</li> </ul>   | Compatible   |
| • Esters                                    | Soluble   | • Stand oil                              | Compatible   |
| • Ketones                                   | Soluble   | Isocyanate                               | Incompatible |
| Glycol-ethers & esters                      | Soluble   | <ul> <li>Urea/melamine resins</li> </ul> | Incompatible |
|                                             |           |                                          |              |

## STORAGE

Solvoya® L3250-ECO is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

## STABILITY

Solvoya® L3250-ECO is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

#### REMARKS

• For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).

• The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.

#### Liquid Coating Resins and Additives

Edition 04-2020

Good gloss & gloss retention

- Very good pigment wetting properties
- · Medium viscosity with high solid alkyd resin
- Very good yellowing resistance

70.0 ± 1.0%

55.0 ± 1.0% 10.0 max. Z1-Z2 at 55% Approx. 3000 CP at 55% 5.0 max.

29% Soya bean oil or Soya Fatty Acid 55% Penta White Spirit

