

## Technical Datasheet

Liquid Coating Resins and Additives

# Solvoya® M5046-W HV

Edition 04-2020

Solvoya® M5046-W HV is a standard medium alkyd resin based on Soya bean oil or Soya Fatty Acid - available in solids of 55% or 60% in White **Mode of application**: Air physical dry

#### PERFORMANCE & APPLICATIONS

<ul> <li>Brushability &amp; leveling</li> </ul>	ζ
---	---

- Very good yellowing resistance & hardness
- Good wetting properties for pigments & fillers

- Enamel undercoat
- Non yellowing air drying enamels
- Quick air drying metal primer & finishes
- Economical stoving enamel (Temp.140-160°C)

#### **SUPPLY SPECIFICATIONS**

- Delivery form
- Dilution form
- Acid value mg KOH/gm solid
- Gardner viscosity at 25°C
- Brookfield approx. viscosity at 25°C
- Gardner Color Scale DIN EN ISO 6271-1

- 60.0 ± 1%
- 55.0 ± 1%
- 10.0 max.
- Approx. Z5-Z6 at 55%
- Approx. 10000 CP at 55%
- 5.0 max.

#### TYPICAL COMPOSITION

- Phthalic anhydride content
- Type of oil
- Oil Content

Type of Polyol

Type of Solvent(s)

- 33%
- Soya bean oil or Soya Fatty Acid
- 50%
- Mixed polyols
- White spirit

#### **SPECIFIC PROPERTIES**

<ul> <li>Aliphatic hydrocarbon</li> </ul>	Soluble
<ul> <li>Aromatic hydrocarbon</li> </ul>	Soluble
<ul> <li>Chlorinated hydrocarbon</li> </ul>	Soluble
<ul> <li>Alcohols</li> </ul>	Insoluble
• Esters	Soluble
• Ketones	Soluble
<ul> <li>Glycol-ethers &amp; esters</li> </ul>	Soluble

- Zinc whiteRed LeadLimited compatibility
- Nitrocellulose Incompatible
- Chlorinated rubber
   Limited compatibility
- Stand oil Incompatible
- Isocyanate
   Incompatible
- Urea/melamine resins
   Limited compatibility

#### **STORAGE**

Solvoya® M5046-W HV is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

### **STABILITY**

Solvoya® M5046-W HV is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

### **REMARKS**

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.