

# Technical Datasheet

Liquid Coating Resins and Additives

# Solvoya® M52300-W

Edition 04-2020

Solvoya® M52300-W is a Chain stopped medium alkyd resin based on Linoleic rich fatty acid - available in solids of 75% in White Spirit.

Mode of application: Air physical dry

### PERFORMANCE & APPLICATIONS

- Excellent recoat-ability properties
- Very fast drying time (Chain stopped medium alkyd resin)
- Very good yellowing resistance & hardness

- Suitable for automotive refinish, machinery & drum paints
- Non yellowing air drying enamels
- Quick air drying metal primer & finishes
- Economical stoving enamel (Temp.140-160°C)

# **SUPPLY SPECIFICATIONS**

- Delivery form
- Dilution form
- Acid value mg KOH/gm solid
- Gardner viscosity at 25°C
- Brookfield approx. viscosity at 25°C
- Gardner Color Scale DIN EN ISO 6271-1

- 75.0 ± 1%
- 75.0 ± 1%
- 12.0 max.
- Approx. Z7-Z8 at 75%
- Approx. 30,000 CP at 75%
- 5.0 max.

## TYPICAL COMPOSITION

- Phthalic anhydride content
- Type of oil
- Oil Content
- Type of Polyol
- Type of Solvent(s)

#### 20%

Linoleic rich fatty acid

48%

Mixed polyols

White spirit

## SPECIFIC PROPERTIES

Glycol-ethers & esters

Aliphatic hydrocarbon	Soluble
Aromatic hydrocarbon	Soluble
<ul> <li>Chlorinated hydrocarbon</li> </ul>	Soluble
• Alcohols	Insoluble
• Esters	Soluble
<ul> <li>Ketones</li> </ul>	Soluble

- Zinc whiteRed Lead
  - Red Lead Limited compatibilityNitrocellulose Incompatible

Limited compatibility

- Chlorinated rubber
   Stand oil
   Limited compatibility
   Incompatible
- Stand oil IncompatibleIsocyanate Incompatible
- Urea/melamine resins
   Limited compatibility

## **STORAGE**

Solvoya® M52300-W is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

# **STABILITY**

Solvoya® M52300-W is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

## **REMARKS**

• For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).

Soluble

• The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.