

Technical Datasheet

Liquid Coating Resins and Additives

Solvoya® N6532-X LS

Edition 04-2020

Solvoya® N6532-X LS is a short oil Non-dry alkyd resin based on Coconut oil - available in solids from 60% to $70\% \pm 2\%$ in Xylene **Mode of application:** Bake, NC and/or catalyzed dry.

PERFORMANCE & APPLICATIONS

 Excellent 	adhecion	and	alnee	اميرما	

- Good mechanical performance
- Good hardness, adhesion and flexibility
- · High viscosity level

- Used for NC-systems, stoving enamels for furniture and automotive refinishes
- Recommended for tinplate varnishes and for furniture lacquers
- Recommended for non-yellowing baking enamels
- Suitable for PU-finishes & general purpose stoving enamels

SUPPLY SPECIFICATIONS

Delivery form

• Dilution form

· Acid value mg KOH/gm solid

Gardner viscosity at 25°C

• Brookfield approx. viscosity at 25°C

• OH-Content (Per solids)

• Gardner Color Scale DIN EN ISO 6271-1

60.0 ± 2%

 $60.0 \pm 2\%$

8.0 max.

Approx. Z2-Z4 at 60%

Approx. 3,200 CP at 60%

3.20%

12.0 max.

TYPICAL COMPOSITION

• Phthalic anhydride content

Type of oil

Oil Content

Type of Polyol

Type of Solvent(s)

44%

Coconut oil

35%

Mixed polyol

Xylene

SPECIFIC PROPERTIES

Aliphatic hydrocarbonAromatic hydrocarbon

Chlorinated hydrocarbon

Alcohols

EstersKetones

Glycol-ethers & esters

Insoluble

Soluble

Soluble Limited solubility

Soluble

Soluble Soluble Zinc white

Red LeadNitrocellulose

• Chlorinated rubber

• Stand oil

IsocyanateUrea/melamine resins

Incompatible

Incompatible Compatible

Incompatible

Limited compatibility
Compatible

Compatible

STORAGE

Solvoya® N6532-X LS is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

STABILITY

Solvoya® N6532-X LS is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

REMARKS

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.