

Technical Datasheet

Liquid Coating Resins and Additives

Solvoya® N6880-X LS

Edition 04-2020

Solvoya® N6880-X LS is short oil non-dry alkyd resin, based on coconut fatty acid, available in solids from 60% to 70% ±2 in xylene.

Mode of application: Bake - Nitrocellulose - Catalyzed dry.

PERFORMANCE & APPLICATIONS

- Excellent adhesion & good gloss.
- · Excellent mechanical performance.
- Excellent yellowing resistance & pigmented wetting properties.
- Excellent color retention.

- Recommended for Urethane 2K PU lacquers & NC lacquers
- Recommended car repair finishes, cellulose nitrate finishes
- Suitable for high quality clear & pigmented NC lacquers
- Suitable for lacquers for furniture & Automotive finishes.
- Suitable for non-yellowing baking enamels.
- Suitable tin plate varnishes.

SUPPLY SPECIFICATIONS

- Delivery form
- Dilution form
- Gardner viscosity at 25°C
- Brookfield approx. viscosity at 25°C
- OH-content (Per solids)
- Gardner Color Scale DIN EN ISO 6271-1
- · Acid value mg KOH/gm solid

- 60.0 ± 2%
- 60.0 ± 2%
- Approx. Z3-Z4 at 60%
- Approx. 8000 CP at 60%
- 2.50%
- 3.0 max.
- 8.0 max.

TYPICAL COMPOSITION

- Phthalic anhydride content
- Type of oil
- Oil Content • Type of Polyol
- Type of Solvent(s)

46%

Coconut fatty acid

32%

Mixed polyols

Xylene

SPECIFIC PROPERTIES

· Aliphatic hydrocarbon · Aromatic hydrocarbon

• Chlorinated hydrocarbon Soluble

Alcohols

Limited solubility Esters Soluble

 Ketones • Glycol-ethers & esters Chlorinated hydrocarbon Soluble Isocyanate

Nitrocellulose

Compatible Compatible

• Urea/melamine resins

Compatible

STORAGE

Solvoya® N6880-X LS is stable at temperatures from 5 °C up to 30 °C when packed in original containers, exposure to sun shine should be avoided. **STABILITY**

Insoluble

Soluble

Soluble

Soluble

Solvoya® N6880-X LS is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

REMARKS

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products