

# Solvoya® UA4027-W

Edition 04-2020

Solvoya® UA4027-W is a polyurethane modified long oil alkyd based on sunflower fatty acid, available in solids of 60±1% in white spirit.

**Mode of application:** Air physical dry

## PERFORMANCE & APPLICATIONS

- Light color with good yellowing resistance
- Excellent abrasion, chemicals & water resistance
- Fast drying time properties
- Excellent compatibility with majority of medium & long alkyds
- Good outdoor durability
- Recommended for varnishes for parquet and furnitures
- Recommended for interior pigmented decorative enamels
- Used for wood varnishes & Yacht varnishes
- Used for out-door wood varnishes (Garden furniture)

## SUPPLY SPECIFICATIONS

- |   |                         |
|---|-------------------------|
| • Delivery form                         | 60.0 ± 1%               |
| • Dilution form                         | 60.0 ± 1%               |
| • Gardner viscosity at 25°C             | Approx. Z1-Z2 at 60%    |
| • Brookfield approx. viscosity at 25°C  | Approx. 2,700 CP at 60% |
| • Gardner Color Scale DIN EN ISO 6271-1 | 2.0 max.                |
| • Acid value mg KOH/gm solid            | 4.0 max.                |

## TYPICAL COMPOSITION

- |                      |                      |
|----------------------|----------------------|
| • Type of oil        | Sunflower fatty acid |
| • Oil Content        | 60%                  |
| • Type of Polyol     | Penta                |
| • Type of Solvent(s) | White spirit         |
| • Type of isocyanate | Aliphatic            |

## SPECIFIC PROPERTIES

- |                           |           |
|---------------------------|-----------|
| • Aliphatic hydrocarbon   | Soluble   |
| • Aromatic hydrocarbon    | Soluble   |
| • Chlorinated hydrocarbon | Soluble   |
| • Alcohols                | Insoluble |
| • Ketones                 | Soluble   |

## STORAGE

Solvoya® UA4027-W is stable at temperatures from 5 °C up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

## STABILITY

Solvoya® UA4027-W is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

## REMARKS

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.